Black pigment FEPREN BP-600 A

MANUFACTURER / SELLER

PRECHEZA a.s.
Nábřeží Dr. E. Beneše 24
751 62 Přerov, Czech Republic
tel.: + 420 581 706 831
fax: + 420 581 706 830
precheza@precheza.cz
www.precheza.cz

PRODUCT INFORMATION		
Iron oxide (Fe ₃ O ₄)		
standard milled black pigment		
very high tinting-strength, hiding power, is not affected by alkalis and proves high		
lightfastness and weather resistance is up to 110°C		
ISO 1248:B III 3 a EC TARIC code 28211000		
77499		
1317-61-9		
215-277-5		
powder		
25 ± 0.2 kgs paper bags or according agreement		
original packaging, dry and covered stores, pile up max. 3 pallets		

Preservation of processing properties six months from the date of expedition is guaranteed by the supplier

RECOMMENDED APPLICATION

Colouring of concrete products like roof tiles, terrazzo, colour floor tiles.

CAN BE ALSO APPLIED FOR

Colouring of cement-based mixtures.

The pigment is not intended for paint producers but application in this sector is possible after succesfull trial tests of the end-user.

Information on application is given in good faith and does not constitute any guarantee. We recommed trial application tests.

TECHNICAL DATA	Unit	Value	Testing method
Fe ₂ O ₃ content	(%)	min. 90.0	SPTM:LM/FE.1
Volatile matters at 105°C	(%)	max. 1.5	SPTM:LM/FE.4
Specific conductivity	(µS/cm)	max. 1500	SPTM:LM/FE.6
pH of aqueous extract		min. 5.0	SPTM:LM/FE.7
Colour shade	according to agreed sample SPTM:LM/FE.10		
	Safety Data She	eet is available on www	v.precheza.cz